

KÖSTER MAUTROL[®] 2C

Tehni ki podaci / Artikal broj
Važi od 07. Januara 2010.

3.061

2 KOMPONENTNA TE NOST NA BAZI SILIKATA ZA PRESECANJE KAPILARNE VLAGE I EG INTEZITETA

OPIS

MAUTROL[®] 2C je 2 komponentna, niskog viskoziteta injekciona te nost na vodenoj bazi alkalsilikata. Sposobnost komponente B da se transformiše u želatinoznu strukturu, omogu ava MAUTROL[®] 2C-u da se injektira i u veoma vlažan zid bez prethodnog dreniranja. On ne stvara samo horizontalnu barijeru protiv rastu e vlage ve i pove ava vrsto u konstrukcije i obezbe uje njenu dodatnu zaštitu protiv agresivnih kontaminacija. MAUTROL[®] 2C nema negativno dejstvo na armaturu.

TEHNI KI PODACI

- Osobina hidroizolater	zaptiva pora /		
- Osnova	alkalsilikat	KOMP. A	KOMP. B
- Boja	plavi	asta	providan
- Spec. gustina Mešavina	1.16 g/ m ²	1.09g/m ²	1.15 g/ m ²
- Inicijalni viskozitet		oko 30 mPas	
- Vreme rada (temp)	oko 30 – 60 min.	(zavisi od temp)	
- Odnos zapremine 9delova/težini	100 delova/ težini		

POLJA APLIKACIJE

MAUTROL[®] je specijalno dizajniran da se injektira metodom malog pritiska, formiraju i horizontalnu barijeru protiv rastu e kapilarne vlage. On tako e oja ava konstrukcije od cigle ili prirodnog kamena. Može se injektirati i sa spoljne i sa unutrašnje strane zida. Tako e se može upotrebiti i samo za oja anje konstrukcije iako nema kapilarne vlage. **Ne može se koristiti u borbi protiv direktnih prodora vode.**

PRIPREMA PODLOGE

Da bi stvorili horizontalnu barijeru, potrebno je na na prvog fugi zida od podloge izbušiti horizontalne rupe 10 – 15 cm me usobnog rastojanja, na 5 cm od kraja debljine zida. Dijametar rupa zavisi od dijametra porta koji se koristi za injektiranje. Pre postavljanja portova o istiti rupe od prašine. Pomešati komponente u odnosu 100 : 9 (mereno po težini), mikserom do postizanja homogene smeše. Injektirati smešu pogodnom pumpom kroz port do potpunog zasi enja podloge. Mogu e je injektiranje vršiti pojedina no ili kroz više portova odjednom. Zamešan MAUTROL[®] je upotrebljiv 45 – 60 min. pre

The accurate and thereby effective and successful application of our products is not subject to our control. The guarantee can therefore only be applied to the quality of our products within the scope of our terms and conditions, not, however, for their effective and successful application. These guidelines replace all previous ones.

nego što otpo ne proces pretvaranja u gel, i za to vreme zamešana koli ina mora da se utroši. Po završetku ukloniti portove i rupe zapuniti sa MAUTROL[®] Borehole Suspension.

POTROŠNJA

Zavisi od kvaliteta podloge i iznosi oko 0.15kg/1 cm debljine zida.

IŠ ENJE ALATA

Odmah po upotrebi o istiti vodom.

PAKOVANJE

Komp. A 262 kg bure, 22 kg kanta
Komp. B 39,5 kg bure, 3,5 kg kanta

SKLADIŠTENJE

uvati na hladnom mestu zašti eno od mraza. Rok upotrebe 2 godine.

Pri radu koristiti zaštitnu opremu!