

# KÖSTER

## BD 50

Tehni ki podaci / Artikal broj

Važi od 14.Januara 2010.

7.09

### BEZ-RASTVARA A,ELASTI NI ZAPTIVA U VLAŽNIM I MOKRIM PROSTORIJAMA ISPOD PLO ICA

#### OPIS

BD 50 je pripremljen za upotrebu, nerastvorljiv i lak za nanošenje (mazanje). On je izuzetan za zaptivanje površine ispod plo ica i pokriva u vlažnim i mokrim prostorijama. Jednom nanešen na podlogu ostavlja visoko fleksibilnu sinteti ku foliju koja je izuzetno elasti na i premoš uje pukotine. BD 50 je pogodan za sve standardne nerastvorljive lepkove za plo ice, kao i za malter.

#### TEHNI CI PODACI

- Viskoznost	3500 mPa.s
- Specifi na težina	oko 1.50 g/cm <sup>3</sup>
- Primena na spoljašnj. temp.	> + 5° C
- Vreme sazrevanja 1. sloja	oko 3 h
- Debljina 1. sloja ( mokrog )	0.5 mm
- Debljina 2. sloja ( mokrog )	0.5 mm
- Vreme sazrevanja 2. sloja ( pre nanošenja plo ica )	oko 20 h
- WDD	7.6 g/ m <sup>2</sup> d
- Dozvoljeno optere enje do loma	2.1 N/ mm <sup>2</sup>
- Dozvoljeno istezanje do pucanja %	220 ( + 23° C )

#### POLJE PRIMENE

BD 50 formira izuzetan dvostruki vodootporni sloj na zidovima i podovima u vlažnim i mokrim prostorijama, na primer u tuš kabinama, kupatilima, servisima za pranje kola i sl. Obezbe uje prijanjanje za beton, zidane zidove, kre no cementrne maltere, porozne betone, eternit plo e, gips, gipsane table i sve vrste kerami kih pokriva a.

#### PODLOGA

Podloga mora biti suva i ista, o iš ena od ulja i masno e, vrsta i ravna i da nije gruba. Podloge sa ve om absorpcijom zahtevaju prajmer Polysil® (oko 130 g/ m<sup>2</sup>). Ne upijaju e podloge zahtevaju prajmerisanje sa BD Prajmerom. U oba slu aja sa ekati oko 3h, pre nanošenja BD 50 sloja.

#### PRIMENA

Promešati BD 50 pre upotrebe i nanositi ga etkom ili valjkom. Preporuka je da se neupijaju e površine obruse pre nanošenja. Uglovi i zid/pod spojevi zahtevaju upotrebu Flex trake K 120 (poliester filc) sa prvim slojem. Naneti drugi sloj preko prvog sloja . Ostaviti da odstoji 20 h pre postavljanja kerami kih plo ica.

#### POTROŠNJA

Po sloju 500 – 600 g/ m<sup>2</sup>  
Ukupna potrošnja 1.0 kg / m<sup>2</sup>

The accurate and thereby effective and successful application of our products is not subject to our control. The guarantee can therefore only be applied to the quality of our products within the scope of our terms and conditions, not, however, for their effective and successful application. These guidelines replace all previous ones.